## **PRODUCT DATA SHEET:**

Product Description : R.C. FOOD LACQUER

Product Type : Epoxy Phenolic

Recommended Uses : Internal & External Food cans & genreal line containers

Excellent Sterlization & Alkali properties.

PRODUCT DATA:

Colour : Gold

% Solid By Weight : 33 +/- 2%

Viscosity @30 Deg C # F4 : 90 +/- 10 sec.

Specific Gravity : 0.98 +/- 0.02

Flash Point : > 25 Deg C.

Self Life : 6 Months.

Acetone & Process Resistance : Satisfactory

APPLICATION:

JAS-ANZ

Substrate : Tin & T.F.S

Application Method : Roller Coating

Thinner : HIM/1100 Cleaning : HIM/1100

Dry Film Weight : 3.5 - 4 mgm./ Sq.Inch

Stoving Schedule : 200 - 205 Deg C for 12 Min.

REMARK: A 2 Coat system with the above lacquer will ensure that any breaks in the 1st Coat are covered by the 2nd Coat. In such cases the 1st Coat should be under baked @170 Deg C for 12 min and the 2nd coat baked at normal schedule (200 Deg C for 12 min). Under this condition dry film weight for 2 coats will be 5 - 6 mgm/sq.inch. Pl note to get optimum properties please ensure PROPER STIRRING of Lacquer before application.

## MANUFACTURED AND QUALITY CONTROLLED UNDER LATEST QUALITY MANAGEMENT SYSTEM.

All details contain in this information sheet have been given to the best of our knowledge and belief. This technical information is intended only as a guide and no binding liability can be derived from it. All information, which refers to working with our products, must be adapted to take account of the local conditions and material used.

Regd. Off: D-501, Serenity, Behind Oshiwara Police Station, Andheri (W.), Mumbai – 400102. India.

Factory: Gut No. 37-B, Viilage Met, Taluka Wada, Dist. Palghar - 421303. India.Tel. No. +91 9270081803 / +919321615557

AN AN ISO 9001: 2008 CERTIFIED COMPANY