



PRODUCT DATA SHEET :

Product Description : R.C. Tube Internal Lacquer
Product Type : Epoxy
Recommended Uses : Internal & External

PRODUCT DATA :

Colour : Pale Gold
% Solid By Weight : 35 +/- 2%
Viscosity @30 Deg C # F4 : 60 Sec. +/- 5 Sec. By B4 at 30 Deg C.
Specific Gravity : 0.97 +/- 0.02
Flash Point : > 25 Deg C.
Self Life : 6 Months.

APPLICATION :

Substrate : Aluminium
Application Method : Roller Coating
Thinner : IS/1001
Cleaning : IS/1001
Dry Film Weight : 7-8 mg / sq inch or 14 -15 micron
Stoving Schedule : 220 Deg C for 12 Min. OR
280 Deg C for 6 Min.

REMARK : A 2 Coat system with the above lacquer will ensure that any breaks in the 1st Coat are covered by the 2nd Coat. In such cases the 1st Coat should be under baked @170 Deg C for 12 min and the 2nd coat baked at normal schedule (200 Deg C for 12 min). Under this condition dry film weight for 2 coats will be 5 - 6 mgm/sq.inch. Pl note to get optimum properties please ensure PROPER STIRRING of Lacquer before application.

MANUFACTURED AND QUALITY CONTROLLED UNDER LATEST QUALITY MANAGEMENT SYSTEM.

All details contain in this information sheet have been given to the best of our knowledge and belief. This technical information is intended only as a guide and no binding liability can be derived from it. All information, which refers to working with our products, must be adapted to take account of the local conditions and material used.