

TUBE PRINTING INKS

Code	Base	Colour	Curing Conditions	Tack	Remarks
TU-Series	Alkyd	Process Colors Pantone Colors Special Colors	120-130°C/ 5 minutes	15 – 20	<ul style="list-style-type: none"> • Depending on the shades, lightfastness of the inks may vary between 1 -8 (Blue Wool Scale) • No heavy metal • Can be printable on all types of substrates & enamels. • Having WET - ON - WET properties.
LF-Series	Alkyd	Process Colors Pantone Colors Special Colors	120-130°C/ 5 minutes	15 – 20	<ul style="list-style-type: none"> • Depending on the shades, lightfastness of the inks may vary between 5-8 (Blue Wool Scale) • No heavy metal • Can be printable on all types of substrates & enamels. • Having WET - ON - WET properties.
OP-Series	Alkyd	Transparent Over printing Varnish	120-130°C/ 5 minutes	10 – 15	<ul style="list-style-type: none"> • Excellent Top Coat Printing Varnish available in Gloss & Matt Finish. • No heavy metal.